

EXHIBIT A



DLA Approved Independent Testing Laboratory

4207-1 Milgen Road, Columbus, GA 31907

Telephone: 844-309-6337

www.textest.com

TextesT Report: 13273
 Date: 6/16/2022
 Page: 1 of 1

CLIENT:

SHEEHAN & ASSOCIATES, P.C.

60 Cuttermill Road
Great Neck, NY 11021

ATTN: Spencer Sheehan

SAMPLE IDENTIFICATION:		BROOKS BROTHERS EUROPE SRL	SHIRT
	SAMPLE #1	FITTED NON-IRON STRETCH	Made in Thailand
		97% Supima/3% Lycra Spandex	
		RN 93966	
		42237-00445 621221 961997 818141120 42112 00189343	

FIBER ANALYSIS:
AATCC 20A*

	#1	#2	Average
Cotton	90.43 %	90.08 %	90.25 %
Spandex	9.57 %	9.92 %	9.75 %

*Based on commercial weight regain

TEXTTEST

signed by



DLA Approved Independent Testing Laboratory

4207-1 Milgen Road, Columbus, GA 31907

Telephone: 844-309-6337

www.texttest.com

TexTesT Report: 13467
 Date: 8/3/2022
 Page: 1 of 3

CLIENT: **SHEEHAN & ASSOCIATES, P.C.**
 60 Cuttermill Road
 Great Neck, NY 11021

ATTN: Spencer Sheehan

SAMPLE IDENTIFICATION:	BROOKS BROTHERS EUROPE SRL		SHIRT
	SAMPLE #1	FITTED NON-IRON STRETCH	Made in Thailand
	97% Supima/3% Lycra Spandex		
	RN 93966		
42237-00445 621221 961997 818141120 42112 00189343			

FITTED NON-IRON STRETCH

FIBER LENGTH AND DISTRIBUTION ASTM D 5103		Length Group Lower Limit (in.)	Number of Fibers	Percent of Total	
		2.040	0	0	
		1.920	0	0	
		1.800	0	0	
		1.680	0	0	
	Extra Long	1.560	1	1	
	Long	1.440	6	6	
	Medium	1.320	9	9	
	Short	1.200	14	14	
		1.080	21	21	
		0.960	21	21	
		0.840	10	10	
		0.720	8	8	
		0.600	8	8	
		0.480	1	1	
		0.360	1	1	
		0.240	0	0	
		0.120	0	0	
		0.000	0	0	
Total			100	100	
Average Length		1.080 "			
Standard Deviation		0.25 %			
Coefficient of Variation		0.227 %			
Maximum		1.629 "			
Minimum		0.409 "			


Probability 25%
 Supima Cotton

TexTesT Report: 13467

Date: 8/3/2022

Page: 2 of 3

BROOKS BROTHERS EUROPE SRL		SHIRT
SAMPLE IDENTIFICATION:	SAMPLE #1	FITTED NON-IRON STRETCH
	97% Supima/3% Lycra Spandex	Made in Thailand
	RN 93966	
	42237-00445	621221 961997 818141120 42112 00189343



SUMMARY COMPARISON 1

Average Length inches	1.080
Std. Deviation	0.245
Coefficient of Variation	0.227 %

American Pima Standard 1.2 to 1.48"

Supima Standard 1.25" to 1.56"

Egyptian ELS Std 1.5" to 2.5"

GIZA 87 93 Std. 1.4 to 1.45"

Short Fiber Content= Less the 0.5"

13467

3 of 3

